Material
95 AU V142

Version	Released on
11	01.04.2026

General Data

Colour: Blue

Physical Properties	**Nominal Range**	**Typical Value**	
Density DIN EN ISO 1183-1, 23 °C	1.2 ±0.02	1.2	g/cm³
Hardness DIN ISO 7619-1, Shore A, 23 °C	94 ±3	94	Shore
Hardness DIN ISO 7619-1, Shore D, 23 °C	46 ±5	46	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	>11	13.8	MPa
Tensile strength DIN 53504, S2, 23 °C	>48	55.0	MPa
Elongation at break DIN 53504, S2, 23 °C	>430	530	%
Tear strength DIN ISO 34-1, B (b), 23 °C		103	KN/m
Compression set DIN ISO 815, 24 h, 70 °C, 10 %		24	%
Compression set DIN ISO 815, 24 h, 100 °C, 10 %		29	%
Glass transition temperature ISO 11357-2, DSC		-36	°C
Torsions pendulum test DIN EN ISO 6721-2A		-22	

Temperature Range

static: -30 to 110 °C

This data sheet supersedes all previous versions. The content is subject to change without prior notice. The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 13.07.2026

Freudenberg FST GmbH
Technology & Innovation Material Compliance
Email: MaterialCompliance@fst.com

Regulatory Material Information for 95 AU V142

This overview reflects the current available conformity documents for this specific material only, applicable at the date of issue identified below, to the best of our knowledge. It is for information purposes only and does not replace the Declarations of Conformity (DoC) or other article or product-based assessments. The DoC are available upon request under the conditions, limitations, and validity periods specified therein.

Overview Material related documents:	**Release Date**	**Expiration Date**
BPA/Phthalate free	28.03.2022	31.12.2027
PFOA / PFOS free	28.03.2022	31.12.2027
ROHS and ELV	28.11.2019	31.12.2027

Issue Date: 13.07.2026

It is valid until the mentioned expiry dates or other legal changes become effective.

Disclaimer:

This declaration supersedes all previous versions. The content is subject to change without prior notice.

These declarations are based on our technical state of the art level of knowledge and the regulations applicable on the date of issuance. Recommendations for use or any other descriptions or technical characteristics do not constitute any kind of warranty or guarantee (within the meaning of §§ 434, 435, 443, 444 or 633, 639 of the German Civil Code (BGB)), whether express or implied, or of any fitness or suitability for a particular purpose. It is the user's sole responsibility to determine whether the provided information is appropriate and complete for its purposes and the intended use.

The user bears any product safety and product liability risk including risks of end users or consumers such as risk or danger for life, body or health including compliance with statutory or other regulatory or administrative requirements or technical norms relevant for the components or end products including e.g. declarations of conformity, certificates, approvals or third-party verifications, requirements regarding CE marking, market or product safety requirements or other regulatory requirements.

Our declarations do not release the user from a careful obligation to check and examine its suitability for its procedures, processes and/or purposes, as well as to examine the possibility of impairing the rights of third parties, if necessary. Insofar and considering that we do not have control how this information is used, we disclaim any liability or warranty whether express or implied.

In all cases, these declarations of conformity remain subject to compliance with the conditions of storage, handling and use in accordance with standard industry practices, as well as good manufacturing practices (GMP), taking into account the specific characteristics of the material or article.

Template Version 1.0 - Any dates are formatted (DD/MM/YYYY)

Freudenberg FST GmbH
Technology & Innovation Material Compliance
Email: MaterialCompliance@fst.com

End of Document

Freudenberg FST GmbH
Technology & Innovation Material Compliance
Email: MaterialCompliance@fst.com