Material
PTFE GM201

Version	Released on
03	14.11.2018

General Data

Colour: Grey

Physical Properties	**Nominal Range**	**Typical Value**	
Density DIN EN ISO 1183-1, 23 °C	2.26 - 2.31	2.28	g/cm³
Hardness DIN ISO 7619-1, Shore D, 23 °C, 3 sec.	60 - 66	62	Shore
Ball indentation hardness DIN EN ISO 2039-1, 23 °C		41	MPa
Tensile strength at break on basis of DIN EN ISO 527, SPI, 23 °C, UR		17	MPa
Elongation at break on basis of DIN EN ISO 527, SPI, 23 °C		293	%

This data sheet supersedes all previous versions. The content is subject to change without prior notice. The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 23.06.2026

Freudenberg FST GmbH
Technology & Innovation Material Compliance
Email: MaterialCompliance@fst.com

End of Document

Freudenberg FST GmbH
Technology & Innovation Material Compliance
Email: MaterialCompliance@fst.com